

Spiralsolution 43125 FSL

Data sheet (heat set fabric)




Württembergische
Spiralsiebfabrik GmbH



Technical Data

Air Permeability:	(cfm)	125
Grammage:	(g/m ²)	1370
Thickness:	(mm)	1,85
Spacing:	(m-1)	187
Ø Monofilament Spiral:	PET	0,43 x 0,70
Ø Monofilament Pintle:	PET	0,70
Size of filler:	PET / P40.1	3,65 x 0,90



Characteristics & Application:

Optimized contact area and high drying capacity

Low thickness

Hydrolysis stabilized

Dryer fabric LWC, SC, News paper

High speed positions PMC

Board with sensitive surface for markings

Spiralsolution 43125 FSL




Württembergische
Spiralsiebfabrik GmbH

Data sheet (heat set fabric)



43000 FSL, 43000 FHL, 43000 FTL, 43000 FLL



Contact Area



36%

Elongation at specific tension
43000 FSL, 43000 FHL, 43000 FTL, 43000 FLL

