


Spiralsolution 60500 SL




Württembergische
Spiralsiebfabrik GmbH

Data sheet (heat set fabric)



Technical Data

Air Permeability:	(cfm)	500
Grammage:	(g/m ²)	1240
Thickness:	(mm)	2,10
Spacing:	(m-1)	192
Ø Monofilament Spiral:	PET	0,60
Ø Monofilament Pintle:	PET	0,70
Size of filler:	PET / P40.1	2,20 x 0,55



Characteristics & Application:

High drying capacity

Stabil runnability

Easy seam closing

Board

Packaging paper


Dryer fabric

Spiralsolution 60500 SL




Württembergische
Spiralsiebfabrik GmbH


Data sheet (heat set fabric)



60000 SL, 60000 HL, 60000 TL, 60000 TL+, 60000 LL, 60000 QL



Contact Area



22%

Elongation at specific tension
60000 SL, 60000 HL, 60000 TL, 60000 TL+, 60000 LL, 60000 QL

