



Spiralsolution 90300 Q

Data sheet (heat set fabric)



Technical Data

Air Permeability:	(cfm)	300
Grammage:	(g/m ²)	2045
Thickness:	(mm)	3,00
Spacing:	(m-1)	144
Ø Monofilament Spiral:	PET-Si Blend	0,90
Ø Monofilament Pintle:	PET	0,90
Size of filler:	PET / P40.1	3,80 x 0,93




Characteristics & Application:


- Abrasion resistant
- High drying capacity
- Stabil runnability
- Conveyor belt
- Dryer fabric
- Slurry dewatering

Spiralsolution 90300 Q


Data sheet (heat set fabric)



90000 S, 90000 H, 90000 T, 90000 T+, 90000 Q, 90000 L



Contact Area



15%

Elongation at specific tension

90000 S, 90000 H, 90000 T, 90000 T+, 90000 Q, 90000 L

