


Spiralsolution 60000 PEEK 7

Data sheet (heat set fabric)



Technical Data

Air Permeability:	(cfm)	950
Grammage:	(g/m ²)	1010
Thickness:	(mm)	2,30
Spacing:	(m-1)	190
Ø Monofilament Spiral:	PEEK	0,60
Ø Monofilament Pintle:	PEEK	0,70
Size of filler:	xxx	xxx



Characteristics & Application:

- Extrem hydrolysis stability up to 240 °C
- Longer lifetime under high temperature conditions
- High drying capacity
- Extrem temperatur positions
- Drying cylinder pressure more than 16 bar (200 °C)
- Tunnel dryer nonwoven, pellets, paint dryer

Spiralsolution 60000 PEEK 7

Data sheet (heat set fabric)

