



Spiralsolution 60400 PPSL

Data sheet (heat set fabric)




Spiralsolution 60400 PPSL

Data sheet (heat set fabric)



Technical Data

Air Permeability:	(cfm)	400
Grammage:	(g/m ²)	1485
Thickness:	(mm)	2,00
Spacing:	(m-1)	180
Ø Monofilament Spiral:	PPS	0,60
Ø Monofilament Pintle:	PPS	0,70
Size of filler:	PET / P40.1	3,00 x 0,76



Characteristics & Application:

- Extrem hydrolysis stability up to 180 °C
- Longer lifetime under high temperature conditions
- Stabil runnability
- Extrem temperatur positions
- Drying cylinder pressure more than 16 bar (200 °C)
- Tunnel dryer nonwoven, pellets, paint dryer

