


QUALITY CONTROL CHART

CUSTOMER Württembergische Spiralsiebfabrik GmbH
POLYMER PEEK
PRODUCT 0.70 / P115S
COLOUR NATURAL
SPOOL DIN 335
LOT NR. A250413

PROPERTIES	TEST METHOD	UNIT	AVERAGE VALUE	AVERAGE DEVIATION
DIAMETER		MM	0.70	
TITLE	DIN EN 1392	DTEX	5040	1.32
BREAKING STRENGTH	DIN EN ISO 2062	N	207	1.45
TENACITY AT BREAK	DIN EN ISO 2062	CN/TEX	41.1	
ELONGATION AT BREAK	DIN EN ISO 2062	%	17.2	0.65
HOT AIR SHRINKAGE TESTRITE 180°C - 2 min - gr.50		%	10.1	± 0.5
HOT AIR SHRINKAGE TESTRITE 200°C - 2 min - gr.50		%	14.5	± 0.5

Date
25/04/2013

Production



Quality Control