

QUALITY CONTROL CHART

CUSTOMER	Württembergische Spiralsiebfabrik GmbH
POLYMER	PEEK
PRODUCT	0,90 / P115S
COLOUR	NATURAL
SPOOL	DIN 335
LOT NR.	A041214

PROPERTIES	TEST METHOD	UNIT	AVERAGE VALUE	AVERAGE DEVIATION
DIAMETER		MM	0,90	
TITLE	DIN EN 1392	DTEX	7800	5,02
BREAKING STRENGTH	DIN EN ISO 2062	N	280	1,58
TENACITY AT BREAK	DIN EN ISO 2062	CN/TEX	35,9	
ELONGATION AT BREAK	DIN EN ISO 2062	%	23,3	2,13
HOT AIR SHRINKAGE TESTRITE 180°C - 2 min - gr.80		%		
HOT AIR SHRINKAGE TESTRITE 200°C - 2 min - gr.80		%	15	± 0.2

Date
22/12/2014

Production

Quality Control

